



Cevi za izmenjivače toplote pema SWG

Outside Diameter  in mm			Standard Wire Gauge (SWG)							
			22 (0.711 mm)	20 (0.914 mm)	18 (1.218 mm)	16 (1.625 mm)	14 (2.032 mm)	12 (2.641 mm)	11 (2.946 mm)	10 (3.251 mm)
			 Weight, kg/m (average wall ¹)							
1/4	0.250	6.350	-	0.12	0.16	0.19	-	-	-	-
5/16	0.313	7.950	-	0.16	0.21	0.26	-	-	-	-
3/8	0.375	9.525	-	0.20	0.25	0.32	0.38	-	-	-
1/2	0.500	12.700	0.21	0.27	0.35	0.45	0.54	0.67	0.72	-
5/8	0.625	15.875	0.27	0.34	0.45	0.58	0.70	0.88	0.95	-
3/4	0.750	19.050	-	0.42	0.54	0.71	0.87	0.11	1.19	1.29
7/8	0.875	22.225	0.38	0.49	0.64	0.84	1.03	1.30	1.42	1.55
1	1.000	25.400	0.44	0.56	0.74	0.97	1.19	1.51	1.66	1.80
1 1/4	1.250	31.750	0.55	0.71	0.93	1.23	1.51	1.93	2.13	2.32
1 1/2	1.500	38.100	0.67	0.85	1.13	1.48	1.84	2.35	2.59	2.84
1 3/4	1.750	44.450	0.78	1.00	1.32	1.74	2.16	2.77	3.06	3.35
2	2.000	50.800	0.89	1.14	1.51	2.00	2.48	3.19	3.53	3.87
2 1/2	2.500	63.500	-	-	1.90	2.52	3.13	4.03	4.47	4.91
3	3.000	76.200	-	-	2.29	3.03	3.77	4.87	5.40	5.94
3 1/2	3.500	88.900	-	-	2.67	3.55	4.42	5.70	6.34	6.97
4	4.000	101.600	-	-	3.06	4.07	5.07	6.54	7.28	8.01

Napomene:

Konvencionalne težine su navedene, pod pretpostavkom da su cevi specificirane sa prosečnim debljinama zida.

Dodati 10% na težinu za minimalne debljine zida cevi.

Množiti navedene težine sa 1.014 za austenitne i dupleks čelike, i sa 0.985 za feritne i martenzitne čelike.