


Dimenzije i težine po metru prema - Precizne cevi - ISO

OD ¹ 	ISO Series	Wall thickness ¹ , mm																													
		0.5	(0.8)	1	(1.2)	1.5	(1.8)	2.0	(2.2)	2.5	(2.8)	3.0	(3.5)	4.0	(4.5)	5.0	(5.5)	6.0	(7.0)	8.0	(9.0)	10.0	(11.0)	12.5	(14.0)	16.0	(18.0)	20.0	(22.0)	25.0	
mm		Weight ² , kg/m (conventional weights)																													
4	2	0.043	0.063	0.074	0.083	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
5	2	0.056	0.083	0.099	0.112	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
6	2	0.068	0.103	0.123	0.142	0.166	0.186	0.197	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
8	2	0.092	0.142	0.173	0.201	0.24	0.275	0.296	0.315	0.339	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
10	2	0.117	0.182	0.222	0.26	0.314	0.364	0.395	0.423	0.462	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
12	2	0.142	0.221	0.271	0.32	0.388	0.453	0.493	0.532	0.586	0.635	0.666	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
12.7	2	0.15	0.235	0.289	0.34	0.414	0.484	0.528	0.57	0.629	0.684	0.718	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
14	3	0.166	0.26	0.321	0.379	0.462	0.542	0.592	0.64	0.709	0.773	0.814	0.906	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
16	2	0.191	0.3	0.37	0.438	0.536	0.63	0.691	0.749	0.832	0.911	0.962	1.08	1.18	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
18	3	0.216	0.339	0.419	0.497	0.61	0.719	0.789	0.857	0.956	1.05	1.11	1.25	1.38	1.5	-	-	-	-	-	-	-	-	-	-	-	-	-	-		
20	2	0.24	0.379	0.469	0.556	0.684	0.808	0.888	0.966	1.08	1.19	1.26	1.42	1.58	1.72	1.85	-	-	-	-	-	-	-	-	-	-	-	-	-		
22	3	0.265	0.418	0.518	0.616	0.758	0.897	0.986	1.07	1.2	1.33	1.41	1.6	1.78	1.94	2.1	-	-	-	-	-	-	-	-	-	-	-	-	-		
25	2	0.302	0.477	0.592	0.704	0.869	1.03	1.13	1.24	1.39	1.53	1.63	1.86	2.07	2.28	2.47	2.64	2.81	-	-	-	-	-	-	-	-	-	-	-		
28	3	0.339	0.537	0.666	0.793	0.98	1.16	1.28	1.4	1.57	1.74	1.85	2.11	2.37	2.61	2.84	3.05	3.26	3.63	3.95	-	-	-	-	-	-	-	-	-		
30	3	0.364	0.576	0.715	0.852	1.05	1.25	1.38	1.51	1.7	1.88	2	2.29	2.56	2.83	3.08	3.32	3.55	3.97	4.34	-	-	-	-	-	-	-	-	-		
32	2	0.388	0.616	0.765	0.911	1.13	1.34	1.48	1.62	1.82	2.02	2.15	2.46	2.76	3.05	3.33	3.59	3.85	4.32	4.74	-	-	-	-	-	-	-	-	-		
35	3	0.425	0.675	0.838	1	1.24	1.47	1.63	1.78	2	2.22	2.37	2.72	3.06	3.38	3.7	4	4.29	4.83	5.33	-	-	-	-	-	-	-	-	-		
38	2	0.462	0.734	0.912	1.09	1.35	1.61	1.78	1.94	2.19	2.43	2.59	2.98	3.35	3.72	4.07	4.41	4.74	5.35	5.92	6.44	6.91	-	-	-	-	-	-	-		
40	2	0.487	0.773	0.962	1.15	1.42	1.7	1.87	2.05	2.31	2.57	2.74	3.15	3.55	3.94	4.32	4.68	5.03	5.7	6.31	6.88	7.4	-	-	-	-	-	-	-		
45	3	-	0.872	1.09	1.3	1.61	1.92	2.12	2.32	2.62	2.91	3.11	3.58	4.04	4.49	4.93	5.36	5.77	6.56	7.3	7.99	8.63	9.22	10	-	-	-	-	-		
50	2	-	0.971	1.21	1.44	1.79	2.14	2.37	2.59	2.93	3.26	3.48	4.01	4.54	5.05	5.55	6.04	6.51	7.42	8.29	9.1	9.86	10.6	11.6	-	-	-	-	-		
55	3	-	1.07	1.33	1.59	1.98	2.36	2.61	2.86	3.24	3.6	3.85	4.45	5.03	5.6	6.17	6.71	7.25	8.29	9.27	10.2	11.1	11.9	13.1	14.2	-	-	-	-		
60	2	-	1.17	1.46	1.74	2.16	2.58	2.86	3.14	3.55	3.95	4.22	4.88	5.52	6.16	6.78	7.39	7.99	9.15	10.3	11.3	12.3	13.3	14.6	15.9	17.4	-	-	-		
70	2	-	1.36	1.7	2.04	2.53	3.03	3.35	3.68	4.16	4.64	4.96	5.74	6.51	7.27	8.01	8.75	9.47	10.9	12.2	13.5	14.8	16	17.7	19.3	21.3	-	-	-		
80	2	-	1.56	1.95	2.33	2.9	3.47	3.85	4.22	4.78	5.33	5.7	6.6	7.5	8.38	9.25	10.1	10.9	12.6	14.2	15.8	17.3	18.7	20.8	22.8	25.3	27.5	-	-		
90	3	-	-	-	2.63	3.27	3.92	4.34	4.76	5.39	6.02	6.44	7.47	8.48	9.49	10.5	11.5	12.4	14.3	16.2	18	19.7	21.4	23.9	26.2	29.2	32	34.5	36.9		
100	2	-	-	-	2.92	3.64	4.36	4.83	5.31	6.01	6.71	7.18	8.33	9.47	10.6	11.7	12.8	13.9	16.1	18.2	20.2	22.2	24.1	27	29.7	31.1	36.4	39.5	42.3		
110	3	-	-	-	3.22	4.01	4.8	5.33	5.85	6.63	7.4	7.92	9.19	10.5	11.7	12.9	14.2	15.4	17.8	20.1	22.4	24.7	26.9	30.1	33.1	37.1	40.8	44.4	47.7		
120	2	-	-	-	-	5.25	5.82	6.39	7.24	8.09	8.66	10.1	11.4	12.8	14.2	15.5	16.9	19.5	22.1	24.6	27.1	29.6	33.1	36.6	41	45.3	49.3	53.2	58.6		
140	3	-	-	-	-	6.13	6.81	7.48	8.48	9.47	10.1	11.8	13.4	15	16.6	18.2	19.8	23	26	29.1	32.1	35	39.3	43.5	48.9	54.2	59.2	64	70.9		
160	2	-	-	-	-	7.02	7.79	8.56	9.71	10.9	11.6	13.5	15.4	17.3	19.1	21	22.8	26.4	30	33.5	37	40.4	45.5	50.4	56.8	63	69.1	74.9	83.2		
180	3	-	-	-	-	-	-	-	-	-	-	-	-	-	21.6	23.7	25.7	29.9	33.9	38	41.9	45.8	51.6	57.3	64.7	71.9	78.9	85.7	95.6		
200	2	-	-	-	-	-	-	-	-	-	-	-	-	-	-	28.7	33.3	37.9	42.4	46.9	51.3	57.8	64.2	72.6	80.8	88.8	96.6	108			
220	3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	36.8	41.8	46.8	51.8	56.7	64	71.1	80.5	89.7	98.6	107	120		
240	3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	40.2	45.8	51.3	56.7	62.1	70.1	78	88.4	98.6	109	133		
260	3	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	43.7	49.7	55.7	61.7	67.5	76.3	84.9	96.3	107	118	129	145

Napomene:

1 Debljine u zgradama treba izbegavati kada je to moguće

2 Konvencionalne težine (ugljenični čelik) su navedene.

Za austenitne nerđajuće čelike množiti navedene težine sa 1.014.

Za feritne i martenzitne čelike množiti navedene težine sa 0.985.